



## Mekaniske verdier - Dørkeplader

Tilstand	Tykkelse mm	Strekfasthet $R_m$ N/mm <sup>2</sup>		0,2% Flytegrense $R_{0,2}$ N/mm <sup>2</sup>	Bruddforlengelse $A_{50mm}$ A		Brinell- hardhet HBS
		min.	maks.	min.	% min.	% min.	
H114	1,5-3	240	310	100	8		60
H114	3-20	240	310	100	10-13	16	60
H244	1,5-3	300	360	220	2		

Alumeco A/S Næsbyvej 26 5000 Odense C Danmark Telefon: +45 6617 8117 Fax: +45 6614 5871 Email: mail@alumeco.dk